


REMARKS

Claims 1-12 are pending in this application. By this Amendment, claims 4, 5, 6, 7, 9 and 10 are amended. No new matter is contained in the amendments.

Please charge any fee deficiency or credit any overpayment to Deposit Account No. 01-2300.

Respectfully submitted,



Robert B. Murray
Registration No. 22,980

Customer No. 004372
AREN'T FOX KINTNER PLOTKIN & KAHN, PLLC
1050 Connecticut Avenue, N.W.,
Suite 400
Washington, D.C. 20036-5339
Tel: (202) 857-6000
Fax: (202) 638-4810

MARKED UP CLAIMS

4. The resin compound used for fabricating the interlayer dielectric of the printed wiring board as set forth in Claim[s] 2
5 [or 3], wherein the polymers having crosslinkable functional groups within a molecule are any one or more of polyether sulfone resin having a hydroxyl group at a terminal, polyvinyl acetal resin having repeated hydroxyl groups within a molecule, and phenoxy resin.

10

5. The resin compound used for fabricating the interlayer dielectric of the printed wiring board as set forth in [any of] Claim[s] 2 [to 4], wherein the phenol novolak epoxy resin curing agent containing triazine rings within a molecule
15 comprises one or two of melamine and benzoguanamine and a compound obtained from a condensation reaction with phenols and formaldehydes and has 5 to 25% by weight of nitrogen content.

6. The resin compound used for fabricating the interlayer dielectric of the printed wiring board as set forth in [any of] Claim[s] 2 [to 5], wherein the maleimide compounds having thermosetting properties are any one or more of
20 N,N'-(4,4-diphenylmethane)bismaleimide,
bis(3-ethyl-5-methyl-4-maleimidephenyl)methane,
25 2,2-bis[4-(4-maleimidephenoxy)phenyl]propane, and thermosetting maleimide compounds obtained from Michael addition reaction of these maleimide compounds and polyamines.

7. A method for producing the resin compound used for fabricating the interlayer dielectric of the printed wiring board as set forth in [any of] Claim[s] 1 [to 6], wherein a
5 composition is made to have 20 to 70 parts by weight of epoxy resins, 5 to 30 parts by weight of polymers having crosslinkable functional groups within a molecule, 10 to 50 parts by weight of maleimide compounds having thermosetting properties, and a balance being a crosslinker added as necessary and a phenol
10 novolak epoxy resin curing agent containing triazine rings within a molecule given that a total amount of the resin compound excluding a solvent is 100 parts by weight, and that a solids content after the composition is added to and dissolved in the solvent becomes 40 to 50% by weight.

15

8. The method for producing the resin compound used for fabricating the interlayer dielectric of the printed wiring board as set forth in Claim 7, wherein the solvent is a mixed solvent of N-methylpyrrolidone and methyl ethyl ketone, the
20 mixing ratio of N-methylpyrrolidone/methyl ethyl ketone being in a range of 50/50 to 40/60 (by weight).

9. A resin sheet for forming an insulating layer used for manufacturing a copper-clad laminate, wherein the resin
25 compound for fabricating the interlayer dielectric of the printed wiring board as set forth in Claim[s] 1 [to 6] is made into a sheet which is in a semi-cured state.

10. A resin applied-copper foil constituted by forming a resin layer on a surface of copper foil employing the resin compound for fabricating the interlayer dielectric of the printed wiring board as set forth in any of Claim[s] 1 [to 6].

11. The copper-clad laminate manufactured by the use of the resin sheet for forming the insulating layer as set forth in Claim 9.

10

12. The copper-clad laminate manufactured by the use of the resin applied-copper foil as set forth in Claim 10.

RECORDED - INDEXED - SERIALIZED - FILED